



**Industrial
&
Marine
Coatings**

1.21

**DTM ACRYLIC
PRIMER/FINISH**

B66W1

PRODUCT INFORMATION

Revised 10/06

PRODUCT DESCRIPTION	RECOMMENDED USES																										
<p>DTM ACRYLIC PRIMER/FINISH is a 100% acrylic emulsion, waterborne, corrosion resistant coating for both new construction and industrial maintenance applications. It can be used as a primer under most water based topcoats or alone as a primer/topcoat system. It can be used directly over multiple substrates.</p> <ul style="list-style-type: none"> • Chemical Resistant • Fast dry • Flash/Early Rust Resistant • Suitable for use in USDA inspected facilities • Early moisture resistant • Outstanding exterior durability 	<p>For use over prepared:</p> <ul style="list-style-type: none"> • Steel • Galvanizing • Aluminum • Masonry • Concrete • Zinc rich primers <p>Examples:</p> <ul style="list-style-type: none"> • Bar Joists • New Construction • Structural Steel • Steel Deck Ceiling • Piping • Tanks <p>Confirms to AWWA D102-03 OCS #3 Acceptable for use in high performance architectural applications.</p>																										
PRODUCT CHARACTERISTICS	PERFORMANCE CHARACTERISTICS																										
<p>Finish: Flat</p> <p>Color: White</p> <p>Volume Solids: 46% ± 2%</p> <p>Weight Solids: 61% ± 2%</p> <p>VOC (EPA Method 24): <150 g/l; 1.25 lb/gal</p> <p>Recommended Spreading Rate per coat:</p> <table border="0"> <tr> <td>Wet mils:</td> <td>5.0 - 10.0</td> </tr> <tr> <td>Dry mils:</td> <td>2.5 - 5.0</td> </tr> <tr> <td>Coverage:</td> <td>150 - 290 sq ft/gal approximate</td> </tr> </table> <p>NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.</p> <p>Drying Schedule @ 6.0 mils wet @ 50% RH:</p> <table border="0"> <thead> <tr> <th></th> <th>@ 55°F</th> <th>@ 77°F</th> <th>@ 120°F</th> </tr> </thead> <tbody> <tr> <td>To touch:</td> <td>1 hour</td> <td>40 minutes</td> <td>20 minutes</td> </tr> <tr> <td>Tack free:</td> <td>6 hours</td> <td>4 hours</td> <td>2 hours</td> </tr> <tr> <td>To recoat:</td> <td>8 hours</td> <td>4 hours</td> <td>2 hours</td> </tr> <tr> <td>To cure:</td> <td>45 days</td> <td>30 days</td> <td>14 days</td> </tr> </tbody> </table> <p>Drying time is temperature, humidity, and film thickness dependent.</p> <p>Shelf Life: 36 months, unopened Store indoors at 40°F to 100°F.</p> <p>Flash Point: >200°F, PMCC</p> <p>Reducer/Clean Up: Water</p>	Wet mils:	5.0 - 10.0	Dry mils:	2.5 - 5.0	Coverage:	150 - 290 sq ft/gal approximate		@ 55°F	@ 77°F	@ 120°F	To touch:	1 hour	40 minutes	20 minutes	Tack free:	6 hours	4 hours	2 hours	To recoat:	8 hours	4 hours	2 hours	To cure:	45 days	30 days	14 days	<p>System Tested: (unless otherwise indicated) Substrate: Steel Surface Preparation: SSPC-SP10 1 ct. DTM Acrylic Primer/Finish @ 3.0 mils dft</p> <p>Abrasion Resistance: Method: ASTM D4060, CS17 wheel, 1000 cycles, 1 kg load Result: 225 mg loss</p> <p>Accelerated Weathering, 2 coats: Method: ASTM D4587, QUV-A, 4,000 hours Results: passes</p> <p>Adhesion: Method: ASTM D4541 Result: >500 psi</p> <p>Corrosion Weathering: Method: ASTM D5894, 12 cycles, 4,032 hours Result: Rating 9 per ASTM D610 for rusting Rating 10 per ASTM D714 for blistering</p> <p>Direct Impact Resistance: Method: ASTM D2794 Result: >140 in. lbs.</p> <p>Dry Heat Resistance: Method: ASTM D2485 Result: 250°F</p> <p>Exterior Durability: Method: 1 year, 45° South Result: Excellent</p> <p>Flexibility: Method: ASTM D522, 180° bend, 1/4" mandrel Result: Passes</p> <p>Moisture Condensation Resistance: (2 coats) Method: ASTM D4585, 100°F, 500 hours Result: Excellent</p> <p>Pencil Hardness: Method: ASTM D3363 Result: H</p> <p>Salt Fog Resistance: (2 coats) Method: ASTM B117, 500 hours Result: Excellent</p> <p>Provides performance comparable to products formulated to federal specification: AA50557, and Paint Specification: SSPC-Paint 23.</p>
Wet mils:	5.0 - 10.0																										
Dry mils:	2.5 - 5.0																										
Coverage:	150 - 290 sq ft/gal approximate																										
	@ 55°F	@ 77°F	@ 120°F																								
To touch:	1 hour	40 minutes	20 minutes																								
Tack free:	6 hours	4 hours	2 hours																								
To recoat:	8 hours	4 hours	2 hours																								
To cure:	45 days	30 days	14 days																								



**Industrial
&
Marine
Coatings**

1.21

DTM ACRYLIC PRIMER/FINISH

B66W1

PRODUCT INFORMATION

RECOMMENDED SYSTEMS	SURFACE PREPARATION								
<p>Steel: 2 cts. DTM Acrylic Primer/Finish @ 2.5 - 5.0 mils dft/ct</p> <p>Steel: 1 ct. DTM Acrylic Primer/Finish @ 2.5 - 5.0 mils dft 2 cts. DTM Acrylic Coating @ 2.5 - 4.0 mils dft/ct or Metalatex Semi-Gloss, @ 1.5 - 4.0 mils dft/ct or Water Based Catalyzed Epoxy @ 2.5 - 3.0 mils dft/ct or SherCryl HPA @ 2.5 - 4.0 mils dft/ct</p> <p>Aluminum, Galvanized, and Masonry: 2 cts. DTM Acrylic Primer/Finish @ 2.5 - 5.0 mils dft/ct</p> <p>Aluminum, Galvanized, and Masonry: 1 ct. DTM Acrylic Primer/Finish @ 2.5 - 5.0 mils dft/ct 2 cts. DTM Acrylic Coating @ 2.5 - 4.0 mils dft/ct or Metalatex Semi-Gloss, @ 1.5 - 4.0 mils dft/ct or Water Based Catalyzed Epoxy @ 2.5 - 3.0 mils dft/ct or SherCryl HPA @ 2.5 - 4.0 mils dft/ct</p> <p>Concrete and Masonry: 1 ct. Heavy Duty Block Filler @ 10.0 - 18.0 mils dft 2 cts. DTM Acrylic Primer/Finish @ 2.5 - 5.0 mils dft/ct</p> <p>Previously Painted Surfaces: 1-2 cts. DTM Acrylic Primer/Finish @ 2.5 - 5.0 mils dft/ct</p> <p>The systems listed above are representative of the products use, other systems may be appropriate.</p>	<p>Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.</p> <p>Do not use hydrocarbon solvents for cleaning.</p> <p>Refer to product Application Bulletin for detailed surface preparation information.</p> <p>Minimum recommended surface preparation:</p> <table border="0"> <tr> <td>Iron & Steel:</td> <td>SSPC-SP2</td> </tr> <tr> <td>Aluminum:</td> <td>SSPC-SP1</td> </tr> <tr> <td>Galvanizing:</td> <td>SSPC-SP1</td> </tr> <tr> <td>Concrete & Masonry:</td> <td>SSPC-SP13/NACE 6 or ICRI 03732, CSP 1-3</td> </tr> </table>	Iron & Steel:	SSPC-SP2	Aluminum:	SSPC-SP1	Galvanizing:	SSPC-SP1	Concrete & Masonry:	SSPC-SP13/NACE 6 or ICRI 03732, CSP 1-3
Iron & Steel:	SSPC-SP2								
Aluminum:	SSPC-SP1								
Galvanizing:	SSPC-SP1								
Concrete & Masonry:	SSPC-SP13/NACE 6 or ICRI 03732, CSP 1-3								
	<h3 style="text-align: center;">TINTING</h3> <p>Tint with Blend-A-Color Toner or EnviroToner at 75% tint strength, 2 oz/gal maximum. Better performance will be achieved with EnviroToners. Product is not controlled for tint strength. Five minutes minimum mixing on a mechanical shaker is required for complete mixing of color.</p> <p>Tinting with Blend-A-Color Toner can affect the flash/early rust resistance of the coating.</p>								
	<h3 style="text-align: center;">APPLICATION CONDITIONS</h3> <table border="0"> <tr> <td>Temperature:</td> <td>55°F minimum, 120°F maximum (air, surface, and material) At least 5°F above dew point</td> </tr> <tr> <td>Relative humidity:</td> <td>85% maximum</td> </tr> </table> <p>Refer to product Application Bulletin for detailed application information.</p>	Temperature:	55°F minimum, 120°F maximum (air, surface, and material) At least 5°F above dew point	Relative humidity:	85% maximum				
Temperature:	55°F minimum, 120°F maximum (air, surface, and material) At least 5°F above dew point								
Relative humidity:	85% maximum								
	<h3 style="text-align: center;">ORDERING INFORMATION</h3> <table border="0"> <tr> <td>Packaging:</td> <td>1 and 5 gallon containers</td> </tr> <tr> <td>Weight per gallon:</td> <td>11.46 ± 0.2 lb</td> </tr> </table>	Packaging:	1 and 5 gallon containers	Weight per gallon:	11.46 ± 0.2 lb				
Packaging:	1 and 5 gallon containers								
Weight per gallon:	11.46 ± 0.2 lb								
	<h3 style="text-align: center;">SAFETY PRECAUTIONS</h3> <p>Refer to the MSDS sheet before use.</p> <p>Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.</p>								
<h3 style="text-align: center;">DISCLAIMER</h3>	<h3 style="text-align: center;">WARRANTY</h3>								
<p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.</p>	<p>The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.</p>								



**Industrial
&
Marine
Coatings**

1.21A

**DTM ACRYLIC
PRIMER/FINISH**

B66W1

APPLICATION BULLETIN

Revised 10/06

SURFACE PREPARATION	APPLICATION CONDITIONS		
<p>Surface must be dry and in sound condition. Remove oil, dust, dirt, loose rust, peeling paint and other contaminants to ensure adequate adhesion.</p> <p>Do not use hydrocarbon solvents for cleaning.</p> <p>Iron and Steel: Minimum surface preparation is Hand Tool Cleaning per SSPC-SP2. Remove all oil and grease from the surface by Solvent Cleaning per SSPC-SP1. For better performance, use Commercial Blast Cleaning per SSPC-SP6. Self priming.</p> <p>Aluminum: Remove all oil, grease, dirt, oxide and other foreign material by Solvent Cleaning per SSPC-SP1. Self priming.</p> <p>Concrete Block: Surface should be thoroughly clean and dry. Air, material and surface temperatures must be at least 55°F before filling. Use Heavy Duty Block Filler. The filler must be thoroughly dry before topcoating.</p> <p>Galvanized Metal: Allow to weather a minimum of 6 months prior to coating. Solvent Clean per SSPC-SP1. When weathering is not possible or the surface has been treated with chromates or silicates, first Solvent Clean per SSPC-SP1 and apply a test area, allowing paint to dry one week before testing adhesion. If adhesion is poor, brush blasting is necessary to remove these treatments. Self priming. Rusty galvanizing requires a minimum of Hand Tool Cleaning per SSPC-SP2.</p> <p>Masonry: All masonry must be free of dirt, oil, grease, loose paint, mortar, masonry dust, etc. Clean per SSPC-SP13/Nace 6/ ICRI 03732, CSP 1-3. Poured, troweled, or tilt-up concrete, plaster, mortar, etc. must be thoroughly cured at least 30 days at 75°F. Form release compounds and curing membranes must be removed by brush blasting. Self priming. Brick must be allowed to weather for one year prior to surface preparation and painting.</p> <p>PVC, Fiberglass: Remove all oil, grease, dirt, and other foreign material by Solvent Cleaning per SSPC-SP1. Scuff sand to abrade surface. Test adhesion.</p> <p>Previously Painted Surfaces: If in sound condition, clean the surface of all foreign material. If paint is peeling or badly weathered, clean surface to sound substrate and treat as a new surface.</p>	<p>Temperature: 55°F minimum, 120°F maximum (air, surface, and material) At least 5°F above dew point</p> <p>Relative humidity: 85% maximum</p> <tr> <th colspan="2" style="text-align: center;">APPLICATION EQUIPMENT</th> </tr> <p>The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.</p> <p>Reducer/Clean Up: Water</p> <p>Airless Spray</p> <p>Pressure 2000 psi Hose 1/4" ID Tip015" - .019" Filter 60 mesh Reduction as needed up to 12-1/2% by volume</p> <p>Conventional Spray</p> <p>Gun Binks 95 Fluid Nozzle 66 Air Nozzle 63PB Atomization Pressure ... 60 psi Fluid Pressure 25 psi Reduction as needed up to 12-1/2% by volume</p> <p>Brush</p> <p>Brush Nylon/Polyester Reduction not recommended</p> <p>Roller</p> <p>Cover 3/8" woven with phenolic core Reduction not recommended</p> <p>If specific application equipment is not listed above, equivalent equipment may be substituted.</p>	APPLICATION EQUIPMENT	
APPLICATION EQUIPMENT			



**Industrial
&
Marine
Coatings**

1.21A

DTM ACRYLIC PRIMER/FINISH

B66W1

APPLICATION BULLETIN

APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Mixing Instructions: Mix paint thoroughly by boxing and stirring before use.

Apply paint at the recommended film thickness and spreading rate as indicated below:

Recommended Spreading Rate per coat:

Wet mils:	5.0 - 10.0
Dry mils:	2.5 - 5.0
Coverage:	150 - 290 sq ft/gal approximate

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 6.0 mils wet @ 50% RH:

	@ 55°F	@ 77°F	@ 120°F
To touch:	1 hour	40 minutes	20 minutes
Tack free:	6 hours	4 hours	2 hours
To recoat:	8 hours	4 hours	2 hours
To cure:	45 days	30 days	14 days

Drying time is temperature, humidity, and film thickness dependent.

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

PERFORMANCE TIPS

Stripe coat all crevices, welds, and sharp edges to protect against early failure in these areas. For best results on rusty surfaces, always apply first coat by brush. No painting should be done immediately after a rain or during foggy weather.

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.

During the early stages of drying, the coating is sensitive to rain, dew, high humidity, and moisture condensation. Plan painting schedules to avoid these influences during the first 16-24 hours of curing.

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.

Excessive reduction of material can affect film build, appearance, and adhesion.

DTM Acrylic Primer/Finish is extremely sensitive to hydrocarbon containing solvents. When cleaning the surface per SSPC-SP1, use only an emulsifying industrial detergent, followed by a water rinse. Do not use hydrocarbon containing solvents.

Do not use oil or alkyd topcoats over DTM Acrylic Primer/Finish.

Do not use hydrocarbon solvents for cleaning.

Refer to Product Information sheet for additional performance characteristics and properties.

CLEAN UP INSTRUCTIONS

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with Mineral Spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using Mineral Spirits.

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.